

Krimpbuis middenwandig

halogeen-vrij krimpverhouding 3:1 met of zonder thermoplastische lijm

De krimpkousen type SR2/SRH2 zijn middenwandig, zonder/met thermoplastische lijm met een krimpverhouding van 3:1. Typische toepassingen zijn druk- en vochtbescherming van kabels, en geschikt voor krimpmoffen en krimpeindsluitingen.



Produktbeschrijving

Artikelbeschrijving	SR2 75-22
Artikelnummer	127406
Notities	De standaardlengtes op de rol kunnen deelstukken bevatten Andere lengtes op aanvraag

Eigenschappen	Toepassing
Middenwandig	Isoleren
Beschrijftbaar	Druk- en vochtbescherming
Bestand tegen chemische invloeden	Geschikt voor krimpmoffen en krimpeindsluitingen
Bestand tegen UV-stralen	
Vrij van oplosmiddelen Eigenschappen	
Niet corrosief	
Niet smeltbaar	
Halogeenvrij	
Zeer goede elektrische eigenschappen	
Hoge trekvastheid	
Koudvloeibestendig (thermisch vormstabiel)	

Technische gegevens

Artikelbeschrijving	SR2 75-22
Artikelnummer	127406
Testrapporten	IEC 60684-2
Materialen	Gemodificeerde polyolefin
	Lood- en cadmiumvrij
Selectie Opmerking	zonder lijm
Lengte L	1 m
Kleuren	zwart
Inner diameter before shrinking (mm)	75 mm
Inner diameter after shrinking (mm)	22 mm
Recovered wall thickness	3 mm
Hardness	55 Shore D
Hardness(associated standard)	DIN 53505
Elongation at break	350 %
Elongation at break (associated standard)	IEC 60684-2
Tensile strength at break	13 MPa
Tensile strength at break (associated standard)	IEC 60684-2
Longitudinal shrinkage	+/- 10 %
Longitudinal shrinkage (associated standard)	IEC 60684-2
Shrink ratio	3 : 1
Shrink ratio (associated standard)	IEC 60684-2
Eccentricity expanded	50 %
Eccentricity recovered	85 %
Eccentricity (associated standard)	IEC 60684-2
Operating temperature range min	-40 °C
Operating temperature range max	120 °C
Operating temperature range (associated standard)	IEC 60684-2
Shrinkage temperature	> 125 °C
Burning behaviour	niet zelfdovend
Burning behaviour (associated standard)	IEC 60684-2
Flexibility at low temperatures	-40 °C
Flexibility at low temperatures (associated standard)	IEC 60684-2
Thermal ageing (168 h at 150 °C): Elongation at break	250 %
Thermal ageing (168 h bei 150 °C): Tensile strength at break	12 MPa
Thermal ageing (168 h bei 150 °C) (associated standard)	IEC 60684-2
Specific volume resistivity	10 ¹⁴ Ω cm
Specific volume resistivity (associated standard)	IEC 60684-2
Dielectric strength	25 kV/mm
Dielectric strength (associated standard)	IEC 60684-2
Corrosion	geen
Corrosion (associated standard)	IEC 60684-2
Resistance to fungus and decay	Tarief 1
Resistance to fungus and decay (associated standard)	IEC 60684-2

Logistieke gegevens

Artikelbeschrijving	SR2 75-22
Artikelnummer	127406
Levering	Warmtekrimpbuis middenwandig als secties
Duurzaamheid aanvullende teksten	Onbeperkt houdbaar
Land van oorsprong	Duitsland
Douanetariefnummer	39173200
EAN/GTIN	4010311024615

Verpakkingsgegevens

Alternatieve maateenheid	Zak	Pallet EW
Basishoeveelheid	5	150
Basis maateenheid	Stuk	Stuk
Lengte (mm)	1050	1200
Breedte (mm)	205	800
Hoogte (mm)	115	1200
Netto gewicht (kg)	1.115	33.45
Bruto gewicht (kg)	1.12	51.65