

Heat shrinkable thick wall tube

halogen-free shrink ratio 3 : 1 with or without adhesive

The heat shrinkable tubes type SR3/SRH3 are thick-walled, without/with thermoplastic adhesive with a shrinkage ratio of 3:1. Typical applications are the protection of cables against moisture and pressure for cables as well as suitable for heat shrinkable joints and terminations.



Product description

Article name	SR3 75-20
Article number	144596
Notes	Other lengths available on request.

Characteristics
Thick wall
Inscribable
Resistant to chemical agents
Stabilized against UV rays
Free from paint-wetting inhibiting substances
Non-corrosive
Infusible
Halogen-free
Superior electrical properties
High tensile strength
Resistant to cold flow (thermally stable)

Applications
Insulating
Protection against moisture and pressure
Suitable for heat shrinkable joints and terminations

Technical data

Article name	SR3 75-20
Article number	144596
Test standards	IEC 60684-2
Materials	Cross-linked polyolefin
	Free of lead and cadmium
Selection Note	without adhesive
Length L	1 m
Colours	black
Inner diameter before shrinking (mm)	75 mm
Inner diameter after shrinking (mm)	20 mm
Recovered wall thickness	4.5 mm
Hardness	55 Shore D
Hardness(associated standard)	DIN 53505
Elongation at break	350 %
Elongation at break (associated standard)	IEC 60684-2
Tensile strength at break	13 MPa
Tensile strength at break (associated standard)	IEC 60684-2
Longitudinal shrinkage	+/- 10 %
Longitudinal shrinkage (associated standard)	IEC 60684-2
Shrink ratio	3 : 1
Shrink ratio (associated standard)	IEC 60684-2
Eccentricity expanded	50 %
Eccentricity recovered	85 %
Eccentricity (associated standard)	IEC 60684-2
Operating temperature range min	-40 °C
Operating temperature range max	120 °C
Operating temperature range (associated standard)	IEC 60684-2
Shrinkage temperature	> 125 °C
Burning behaviour	not self-extinguishing
Burning behaviour (associated standard)	IEC 60684-2
Flexibility at low temperatures	-40 °C
Flexibility at low temperatures (associated standard)	IEC 60684-2
Thermal ageing (168 h at 150 °C): Elongation at break	250 %
Thermal ageing (168 h bei 150 °C): Tensile strength at break	12 MPa
Thermal ageing (168 h bei 150 °C) (associated standard)	IEC 60684-2
Specific volume resistivity	10 ¹⁴ Ω cm
Specific volume resistivity (associated standard)	IEC 60684-2
Dielectric strength	25 kV/mm
Dielectric strength (associated standard)	IEC 60684-2
Corrosion	none
Corrosion (associated standard)	IEC 60684-2
Resistance to fungus and decay	Rate 1
Resistance to fungus and decay (associated standard)	IEC 60684-2

Logistics data

Article name	SR3 75-20
Article number	144596
Delivery scope	Thick wall heat shrinkable tube in lengths
Shelf life description	Unlimited shelf life
Country of origin	Germany
Customs tariff number	39173200
EAN/GTIN	4010311009605

Packaging data

Alternative unit of measure	Bag	Pal. OW
Base quantity	5	150
Base unit of measure	Piece	Piece
Length (mm)	1030	1200
Width (mm)	260	800
Height (mm)	125	1200
Net weight (kg)	1.6	48
Gross weight (kg)	1.605	66.2