


Gaine thermorétractable à paroi épaisse

rapport de rétreint 3 : 1 avec adhésif

Les gaines thermorétractables de type SRFH3 sont à paroi épaisse, avec colle thermoplastique, avec un rapport de rétreint 3:1. Les domaines d'application typiques sont la protection des câbles contre les résistante à la pression et à l'humidité, ainsi que l'utilisation dans les boîtes de jonctions et extrémités thermorétractables.



Description du produit

Nom de l'article	SRFH3 30-8
Numéro d'article	144527
Notes	D'autres longueurs sur demande.

Caractéristiques
A paroi épaisse
Marquable
Résistant aux influences chimiques
Stabilisé contre les rayons UV
Exempt de substances qui peuvent gêner les opérations de peinture
Non corrosif
Infusible
Très bonnes propriétés électriques
Haute résistance à la traction
Résistant au fluage (stabilité thermique)
Auto-extinguible

Application
Isolation
Protection résistante à la pression et à l'humidité
Pour boîtes de jonctions et extrémités thermorétractables

Données techniques

Nom de l'article	SRFH3 30-8
Numéro d'article	144527
Norme	IEC 60684-2
Matériaux	Polyoléfine réticulée
	Sans plomb ni cadmium
Sélection Indication	barres
Longueur L	1 m
Couleurs	noir
Inner diameter before shrinking (mm)	30 mm
Inner diameter after shrinking (mm)	8 mm
Recovered wall thickness	3.5 mm
Hardness	51 Shore D
Hardness (associated standard)	DIN 53505
Elongation at break	350 %
Elongation at break (associated standard)	IEC 60684-2
Tensile strength at break	13 MPa
Tensile strength at break (associated standard)	IEC 60684-2
Longitudinal shrinkage	+/- 10 %
Longitudinal shrinkage (associated standard)	IEC 60684-2
Shrink ratio	3 : 1
Shrink ratio (associated standard)	IEC 60684-2
Eccentricity expanded	50 %
Eccentricity recovered	85 %
Eccentricity (associated standard)	IEC 60684-2
Shrinkage temperature	> 125 °C
Burning behaviour	auto-extinguible
Burning behaviour (associated standard)	IEC 60684-2
Flexibility at low temperatures	-40 °C
Flexibility at low temperatures (associated standard)	IEC 60684-2
Thermal ageing (168 h at 150 °C): Elongation at break	250 %
Thermal ageing (168 h bei 150 °C): Tensile strength at break	12 MPa
Thermal ageing (168 h bei 150 °C) (associated standard)	IEC 60684-2
Operation temperature min	-40 °C
Operation temperature max	120 °C
Operation temperature (associated standard)	IEC 60684-2
Specific volume resistivity	10 ¹⁴ Ω cm
Specific volume resistivity (associated standard)	IEC 60684-2
Dielectric strength	25 kV/mm
Dielectric strength (associated standard)	IEC 60684-2
Corrosion	rien
Corrosion (associated standard)	IEC 60684-2
Resistance to fungus and decay	Niveau 1
Resistance to fungus and decay (associated standard)	IEC 60684-2

Données logistiques

Nom de l'article	SRFH3 30-8
Numéro d'article	144527
Volume de livraison	Gaine thermorétractable à paroi épaisse en barres
Conservation textes supplémentaires	Stockage illimité
Pays d'origine	Allemagne
Numéro de tarif douanier	39173900
EAN/GTIN	4010311010007

Données d'emballage

Alternative unité de mesure	Sachet1	Sachet
Quantité de base	1	10
Base unité de mesure	Pièce	Pièce
Longueur (mm)	1000	1200
Largeur (mm)	46	300
Hauteur (mm)	25	250
Poids net (kg)	0.138	1.38
Poids brut (kg)	0.138	1.385